



**Table I**  
**Summary of Core Testing**

**JOB NO.** 22-8-111

Core No.	LOCATION Trails at Crowfoot Filing 12 - Coring Parker, CO	Design Thickness (inches)	Core Thickness (inches)	Max Theo. Unit Wt. (1) (pcf)	Core Unit Wt. (2) (pcf)	Percent Compact. (3) (%)	Specified Compaction. (%)
1	Beebalm Loop	5.0	5.3	152.95	145.9	95.4	92-96
2	Beebalm Loop	5.0	5.7	152.95	146.3	95.7	92-96
3	Beebalm Loop	5.0	5.3	152.95	144.5	94.5	92-96
4	Beebalm Loop	5.0	5.4	152.95	146.0	95.5	92-96
5	Beebalm Loop	5.0	5.0	152.95	147.0	96.1	92-96
6	Beebalm Loop	5.0	5.8	152.95	146.9	96.1	92-96
7	Beebalm Loop	5.0	5.8	152.95	145.3	95.0	92-96
	Average		5.47		146.0	95.5	

Notes:

1. Mix Design: Schmidt: Grading ¾" NMAS & Grading ½" NMAS
2. Core unit weight determined in Kumar and Associates Lab.
3. 92% to 96% of maximum theoretical density.
4. Minimum thickness of 5 inches.